



Richmond - Backfill Sand

Sand

Dutra Materials' Backfill Sand is of a hard and durable nature. It is classified as a poorly graded sand (SP) using ASTM D2487, and will be free of deleterious material.

<u>Sieve Size</u>	<u>Typical Gradation</u>
No. 4 (4.75mm)	100
No. 8 (2.36mm)	73
No. 16 (1.18mm)	62
No. 30 (600um)	47
No. 50 (300um)	29
No. 100 (150um)	17
No. 200 (75um)	10

NOTE: All third-party sampling of aggregate for the purpose of specification compliance shall be performed in accordance with California Test Method 125. Testing of these materials for compliance purposes shall be done in accordance with applicable California Department of Transportation test methods and practices.

Matthew James

Matthew James
Quality Control